



1029

NIS a.d. Novi Sad, Refining

Spoljnostarcevačka 199, 26 000 Pancevo Serbia

15

DOP-005

www.nis.rs/product/bitumen

EN 14023:2010

Polymer modified bitumen: 25/55-55

Intended to be used for paving applications

Penetration at 25°C	25 – 55 x 0,1mm
Softening point	≥ 55 °C
Force ductility	≥ 0,5 J/cm ² at 15 °C
Resistance to hardening at 163°C (EN 12607-1)	
Retained penetration at 25°C	≥ 60%
Increase in softening point	≤ 12°C
Drop in softening point	TBR
Fraass breaking point	≤ -10°C
Elastic recovery at 25°C	≥ 50%