



1029

**NIS a.d. Novi Sad, Refining**

Spoljnostarcevacka 199, 26 000 Pancevo Serbia

18

DOP-006

[www.nis.rs/product/bitumen](http://www.nis.rs/product/bitumen)

**EN 12591:2009**

*Paving grade bitumen: 35/50*

*Intended to be used for paving applications*

Penetration at 25°C	35 – 50 x 0,1mm
Softening point	50 – 58°C
Resistance to hardening at 163°C (EN 12607-1)	
Retained penetration at 25°C	≥ 55%
Increase in softening point	≤ 8°C
Penetration index	-1,5 to +0,7
Fraass breaking point	≤ -5°C
Dynamic viscosity at 60°C	≥ 225 Pa·s