



1029

NIS a.d. Novi Sad, Refining

Spoljnostarcevaccka 199, 26 000 Pancevo Serbia

11

DOP-003

www.nis.rs/product/bitumen

EN 12591:2009

Paving grade bitumen: 160/220

Intended to be used for paving applications

Penetration at 25°C 160 – 220 x 0,1mm

Softening point 35 – 43°C

Resistance to hardening at 163°C (EN 12607-1)

Retained penetration at 25°C ≥ 37%

Increase in softening point ≤ 12°C

Penetration index -1,5 to +0,7

Fraass breaking point ≤ -15°C

Dynamic viscosity at 60°C ≥ 30 Pa·s